

## Coeman Packaging NV

### Technische Fiche – Fiche Technique – Technical Data

#### FILM ETIRABLE MANUEL REF. 360

Dimensions : 500 mm x 300 m  
Couleur : transparent  
Epaisseur : 22 my

Property	Units	Value	Test Method
M.F.I. (kg 2,16 – T 190° C)	gr/10'	2,5	D1238
Density	gr/cm <sup>3</sup>	0.918	ASTM D1505
Tensile strength at break Longitudinal Transversal	N/mm <sup>2</sup> N/mm <sup>2</sup>	30 +/-10% 17 +/-10%	ASTM D882 ASTM D882
Yield strength Longitudinal Transversal	N/mm <sup>2</sup> N/mm <sup>2</sup>	9 +/-10% 8 +/-10%	ASTM D882 ASTM D882
Elongation at break Longitudinal Transversal	% %	390 +/-15% 650 +/- 15%	ASTM D882

Stretch film obtained by Linear Polyethylene atossic (D.M. 21/03/1973 and following) and 100% recyclable.

Note : The data described in this sheet don't create any liability, warranty or guarantee for our enterprise.

Tolérances : - Longueur : ca 3%  
- Epaisseur : ca 1 my  
- Largeur : ca 3%