

Coeman Packaging NV

Technische Fiche – Fiche Technique – Technical Data

POWERSTRETCH NEO 430-700 - 12 MY

Mechanical Properties	Units	Value	Tolerance	Test Method
UTS MD	N/mm ²	47	+/- 15 %	ASTM-D882
UTS TD	N/mm ²	39	+/- 15 %	ASTM-D882
Elongation at Break MD	%	407	+/- 15 %	ASTM-D882
Elongation at Break TD	%	575	+/- 15 %	ASTM-D882
Puncture	Gr*cm/μ	1690	+/- 15 %	ASTM-D5748
Prestretch CPIT	% %	200 270	+/- 15 % +/- 15 %	
Elmendorf Tear MD	Gr	79	+/- 15 %	ASTM-D1922
Elmendorf Tear TD	Gr	414	+/- 15 %	ASTM-D1922